

Vizela

Specifications

Product Category: Privacy	Composition: 100% fiberglass / EVA coating
Openness Factor: 1%	Standard Packaging: Rolls of 36 ly (33 lm)
UV Blockage: Approximately 99%	Width: 94.5" (240 cm)
Fabric Style: Rib Weave	Weight: 8.7 oz / yd2 (295 g / m2) ± 5%
Item #: 011600	Thickness: .013" (0.35 mm) ± 5%



Fenestration Data

Color#	Color Name	Fabric Properties					Fabric & Glass		Illuminance	
		Thermal			Optical		Commercial	Residential	Blackout %	Glow %
		Total Solar			Rv (%)	Tv (%)	SHGC % Improvement	SHGC		
Rs (%)	As (%)	Ts (%)								
000618	Mississippi	52	15	33	51	32	37	0.42	0	100
000623	Sahel	53	14	33	53	32	39	0.42	0	100
000609	Loutre	21	67	12	18	10	21	0.54	0	100
000600	Blanc	59	5	36	61	37	42	0.39	0	100
000608	Chartreux	37	40	23	34	20	29	0.48	0	100

The fabric performance tests were conducted in accordance with ASTM E891 & ASTM E903-96: Total Solar Transmittance (Ts), Total Solar Reflectance (Rs), Total Solar Absorptance (As), Visible Reflectance (Rv), and Visible Transmission (Tv). Glass performance tests for Solar Heat Gain Coefficient (SHGC) were conducted using the Lawrence Berkeley National Laboratory Window 7.3 NFRC certified software. SHGC % improvement for commercial applications is based on a standard commercial glass makeup of Double Glazing 6 mm / 1/2" air / 6 mm with low E on surface #2. SHGC for residential applications is based on a default residential glass makeup of 3mm clear glass / 1/2" air / 3mm clear glass. Results for SHGC were obtained using the center of glass. Acoustical performance was tested in accordance with ASTM C423-09a: NRC is Noise Reduction Coefficient, SAA is Sound Absorption Average. For up-to-date test results, performance specifications and larger samples, contact the Mermet Technical Department at: www.mermetusa.com.

Fabrication Methods:

Cutting: cold, ultrasonic or crush
 Welding: radio frequency, high frequency, impulse, hot air, wedge. May require the use of welding tape. Please contact Mermet for more information regarding our welding tape product line.

We recommend testing all cutting and welding methods prior to use to confirm they meet your individual fabrication specifications.

Fire Classifications:

NFPA 701-10 TM#1, California U.S. Title 19
 CAN/ULC-S109-03 Small & Large Flame Test

Bacterial and Fungal Resistance:

ASTM E2180, ASTM G21

Environmental Benefits:

RoHS - Lead Free

Acoustical Performance:

NRC: 0.35, SAA: 0.33

Care & Handling

Remove dust with vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. For spot removal, a natural or dry cleaning sponge may be used.

5970 N. Main Street • Cowpens, SC 29330

Sales Department: Ph (866) 902-9647

info@mermetusa.com